



M26500

LINEAR LOW DENSITY POLYETHYLENE HIGH FLOW GRADE

M 26500 is a butene comonomer based Linear Low Density Polyethylene grade with narrow molecular weight distribution and optimum levels of antioxidants. It offers excellent processability and is mainly recommended for preparing masterbatch. This grade can also be used for producing injection moulded lids, containers, houseware & general purpose articles as it exhibits good flexibility, low warpage and good fluidity.

Typical Characteristics*			
Property	Test Method	Unit	Typical Value**
Density (23°C)	ASTM D1505	g/cc	0.926
MFI (190°C/2.16 Kg)	ASTM D1238	g/10 min	50
Tensile Yield Strength	ASTM D638	MPa	11.5
Elongation at Break	ASTM D638	%	600
Flexural Modulus	ASTM D790	MPa	250
Softening Point	ASTM D1525	°C	97

*Typical Characteristics and not to be taken as specifications

**Mechanical Properties are on Injection Moulding Specimen

Applications

Masterbatches, shopping baskets, lids, hot melt adhesives, powder coating.

Regulatory Information

- Meets the requirements stipulated in standard IS : 10146 on "Specification for Polyethylene for safe use in contact with foodstuffs, pharmaceuticals, and drinking water". It also conforms to the positive list of constituents as prescribed in IS : 10141. The grade and the additives incorporated in it also comply with the FDA:CFR Title 21, 177.1520, Olefin polymers.

Storage Recommendations

- Bags should be stored in dry / closed conditions at temperatures below 50°C and protected from UV / direct sunlight.

Reliance Industries Limited, Product and Application Technology Group.

Swastik Mill Compound, VN. Purav Marg, Chembur, Mumbai-400 071. Tel.: +91-22-6767 7000. E-mail: polymer_patsupport@ril.com Website: www.ril.com

• The information and data presented herein is true and accurate to the best of our knowledge. No warranty or guarantee expressed or implied, is made regarding performance or otherwise. This information and data may not be considered as a suggestion to use our products without taking into account existing patents, or legal provisions or regulations, whether national or international. • The user of any information and/or data is advised to obtain the latest details from any of the offices of the company or its authorised agents, as the information and/or data is subject to change based on the research and development work undertaken by the company.

Updated as of May, 2007