



LL36RA045

LINEAR LOW DENSITY POLYETHYLENE ROTOMOULDING APPLICATION

LL36RA045 is a Butene Comonomer based Linear Low Density Polyethylene. This grade when blended with appropriate quantity of carbon black can withstand continuous outdoor exposure. LL36RA045 when pulverised into 20-30 mesh powder offers good processability. This grade has very good Environmental Stress Crack Resistance (ESCR) and a combination of hardness and impact strength. This grade contains normal dose of antioxidant.

Typical Characteristics*		
Test Method	Unit	Typical Value
ASTM D1238	gm/10 min	4.5
ASTM D1505	gm/cm³	0.936
ASTM D638	MPa	18
ASTM D638	%	20
ASTM D790	kg/cm²	6,000
ASTM D256	kg.cm/cm	25.0
ASTM D1693	hr	>350
ASTM D2240	D	55
ASTM D1525	°C	117
	ASTM D1238 ASTM D1505 ASTM D638 ASTM D638 ASTM D790 ASTM D256 ASTM D1693 ASTM D1693 ASTM D2240	ASTM D1238 gm/10 min ASTM D1505 gm/cm³ ASTM D638 MPa ASTM D638 % ASTM D790 kg/cm² ASTM D256 kg.cm/cm ASTM D1693 hr ASTM D2240 D

^{*}Typical Characteristics and not to be taken as specifications

Applications

Overhead water tank, loft tank, litter bin etc.

Regulatory Information

Meets the requirements stipulated in standard IS: 10146 on "Specification for Polyethylene for safe use in contact with foodstuffs, pharmaceuticals, and drinking water". It also conforms to the positive list of constituents as prescribed in IS: 10141. The grade and the additives incorporated in it also comply with the FDA:CFR Title 21,177.1520, Olefin polymers.

Storage Recommendations

• Bags should be stored in dry/closed conditions at temperatures below 50°C and protected from UV/direct sunlight.

Reliance Industries Limited, Product and Application Technology Group.

 $Swastik\ Mill\ Compound,\ V.N.\ Purav\ Marg,\ Chembur,\ Mumbai-400\ 071.\ Tel.: +91-22-6767\ 7000.\ E-mail:\ polymer_patsupport@ril.com\ Website:\ www.ril.com\ Marg,\ Chembur,\ Mumbai-400\ 071.\ Tel.:\ Polymer_patsupport@ril.com\ Website:\ Www.ril.com\ Website:\ Www.ril.com\ Website:\ Www.ril.com\ Website:\ Website:\ Www.ril.com\ Website:\ Websit$

^{1.} Compression moulded test specimen (2.0 mm thick)

^{2.} Compression moulded test specimen (3.2 mm thick)

^{3.} Injection moulded test specimen (3.2 mm thick)